

---

## Technical Bulletin AG-01

### AG-400™ Anti-Glare Coating

#### Description

**AG-400™** is a primer free, permanent **anti-glare** coating applied in-house to plastic substrates. This coating reduces reflected glare from light sources, thereby enabling a clearer view of the underlying printing, panel, or artwork. This allows the underlying display to be read quickly, comfortably, and clearly.

**Anti-Glare** deals with **external** sources of reflection off a surface – excessive glare impacts the readability of the image or information being displayed. **AG-400™** uses diffusion mechanisms to break up the reflected light from the viewing surface to the observer. Diffusion works by reducing the coherence of the reflected image, thereby reducing the interference with viewing of the intended image contained in the display.

#### Applications

**AG-400™ Anti-glare** coated plastics can be used wherever surface glare is a concern. The application is a low temperature process, producing a tough crosslinked scratch resistant matrix. Ideal applications include instrument gauges, artwork, digital displays, and other transparent plastic surfaces where reflected glare is an issue.

The anti-glare sheet should be positioned as close as possible to the surface being viewed to obtain a clear image. An excessive air gap would reduce the clarity of the image proportional to the distance. ½ inch or less is recommended.

#### Properties

**Coating Adhesion (ASTM D3359)** - No coating removal in standard crosshatch tape pull adhesion testing.

**Gloss (ASTM D523)** - 50 ± 5

**Good Hardness and Abrasion Resistance** - Substantial improvement in the abrasion resistance of the coated plastic's surface.

**Transmittance (ASTM D1003)** - 89 ± 2

#### Cleaning Instructions

The **AG-400™ Anti-glare** coating is hydrophobic, soil and scratch resistant. If the surface has been subjected to contaminating conditions, observe the following cleaning instructions to maintain the function and integrity of the coating:

Clean with water, mild glass cleaners that do not leave a residue or a solution of mild dishwashing soap and water, rinse with water after cleaning. Dry with a clean, soft microfiber cloth - **Do not** rub dry with coarse paper towels or soiled towels as this can scratch the surface and eventually wear off the coating. Do not use cleaning agents containing an abrasive.

#### Product Availability

**AG-400™ Anti-glare** coating can be applied to many clear & tinted plastics including acrylics, polycarbonate, PETG, PET, PVC, and polystyrene. It is applied on one side or it can be combined with SciCron Technologies' **C-300™ ESD** coating or **Mar-Con® 550 Hard Coat** for a two-side coated product. Coating application drying conditions dictate anti-glare efficiency, maximum trimmed sheet size is 48"x118". Smaller sizes are also available. **AG-400™ Anti-glare coating can also be custom coated to customer supplied sheets, parts, and assemblies.**

AG-01-2/3/18

The information and statements contained herein are believed to be accurate, however, users should perform their own testing and verification to determine the durability, applicability and suitability of the products for their own purposes. NOTHING CONTAINED HEREIN SHALL BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED. IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE HEREBY EXCLUDED. All sales are subject to SciCron's standard terms and conditions of sale, which can be found at: <http://www.sctech.com/termscon>